



Kevin Dyes & Chemicals Pvt. Ltd.

Corporate Office
304/305, G-24 Gundecha Industrial Complex, Akurli Road, Kandivali (East) Mumbai - 400 101, INDIA
Phone: + 91 22 2884 6582/2884 6583/2884 6564/2884 6586 • Fax: + 91 22 2887 6419
Email: kevin@kevinindia.in • Website: www.kevinpigments.com • Website: www.kevinindia.in

Branch Office
15, Indu Chambers, Second Floor, 349/53, Samuel Street, Masjid Bunder, Mumbai - 400 003, INDIA
Phone: + 91 22 2342 2940/2347 2941/40 • Fax: + 91 22 2343 8058 • Email: kevin@kevinindia.in

Works

Plot No. 3105, 06, 07 GIDC Estate, phase III Ranoli - 394 116 Dist: Bharuch (State: Gujarat), INDIA	Plot No. 6726 GIDC Estate Dist: Bharuch Ankleshwar-393 002 (State: Gujarat), INDIA	C-1/4761 GIDC Estate Dist: Bharuch Ankleshwar-393 002 (State: Gujarat), INDIA	Plot No. 6908, 09, 10 GIDC Estate Ankleshwar-393 002 (State: Gujarat), INDIA
---	--	---	---




Environment is our Inspiration

Pigment for
INK



Kevin Dyes & Chemicals Pvt. Ltd.



The future will either be
Green / Blue or not at all



KEVIN
means Worldwide Winner

Printing Paste					Application	
Resistance					Printing	Textile
Light Fastness	Heat Resistance	Acid Fastness	Alkali Fastness	Fastness Properties		
7-8	180	5	5		★	★
7-8	180	5	5		★	★
7-8	280	5	5		★	
7-8	280	5	5		★	★

Special Ink										Application	
Resistance										Photoresist	Textile
Light Fastness	Heat Resistance	Acid Fastness	Alkali Fastness	Cyclohexanone Fastness	PGMEA Fastness	N-butanol Fastness	Butanone Fastness	Ethyl acetate Fastness	Fastness Properties		
7-8	280	5	5	5	5	5	5	5			★
7-8	280	5	5	5	5	5	5	5			★
7-8	280	5	5	5	5	5	5	5			★ ★

Remarks: ★ Applicable ☆ Indicates that it is applicable under certain conditions, it is recommended test first



KEVIPOUND PIGMENT

Printing Paste								
Series	Colour Index No.	Full Shade	Reduced Shade	Physical Properties				
				Density g/cm ³	Specific Surface (area m ² /g)	PH Value	Oil Absorption g/100g	Conductivity us/cm
Phthalocyanine Blue	P.B.15			1.61	60	6.0-9.0	35-45	≤500
				1.60	61	6.0-8.0	35-45	≤500
701883	P.B.15:3			1.59	62	6.0-8.5	40-55	≤300
Phthalocyanine Green	7049G	P.G. 7		1.87	60	6.5-8.0	32-42	≤300

Special Ink								
Series	Colour Index No.	Full Shade	Reduced Shade	Physical Properties				
				Density g/cm ³	Specific Surface (area m ² /g)	PH Value	Oil Absorption g/100g	Conductivity us/cm
Phthalocyanine Blue	P.B.15:3			1.59	62	6.0-8.5	35-55	≤300
				1.62	80	6.5-8.5	40-55	≤300
1500086	P.B.15:6			1.62	80	6.5-8.5	40-55	≤300
Phthalocyanine Green	7055G	P.G.7		1.87	60	6.5-8.0	32-42	≤300

Note: The data in this sheet results from our company's testing system. Please check the data when you apply the product in different system. Solvent fastness: 1-5, light fastness: 1-8, Detection of heat resistance is PP 5 minutes, Acid fastness: 1-5, Alkali fastness: 1-5



Alpha & Beta Blue Plant



Yellow Plant



Vinod Mehta, Chairman

Our Vision. Our Mission.

To attain leadership by building customer satisfaction through fairness and quick response providing innovative products and services suited to customer needs, remaining driven by technology and cost conscious thereby sustaining our valuable niche in the market.

To provide quality products that add value to our customers' businesses. To constantly strive to develop and deliver innovative solutions that meet and exceed our customers' needs and to accomplish this while meeting or exceeding the Company's financial goals.

Our Company. Our Competence.

KEVIN (India) is a reputed company engaged in the manufacture of Pigment Powder for Paints, Plastics, Ink, Cosmetics and Textiles. The Company was established in 1995 and is ISO 9001-2008 also 22000 - 2005 certified. It has a solid customer base in over 36 countries across the world.

Initially set up to produce reactive dyes for textiles, the Company has since grown into a reliable supplier of various dyestuffs, chemicals and Phthalo pigments for the international market.

Advanced technology, strict quality control systems and advanced management systems are today the hallmark of the Company. It has strong capabilities in the areas of technical support and quality control. The company's R&D centre comprises a first class lab and 25 resident technicians. This facility communicates and stays abreast of the latest advances in technology through co-operation with specialty laboratories and scholars.

The company has established a global marketing network and leverages its professional knowledge to provide consultancy services to its customers. Advanced logistics capabilities ensure that we can deliver our products on time anywhere in the world. Our ability to supply quality products consistently through sustained innovation has made us a force to reckon with in the international market.



Green-7 Plant



CPC Blue Plant



Kevin Mehta, M.D



KEVIPOUND PIGMENT

Offset Ink								
Series	Colour Index No.	Full Shade	Reduced Shade	Physical Properties				
				Density g/cm ³	Specific Surface (area m ² /g)	PH Value	Oil Absorption g/100g	Conductivity us/cm
Phthalocyanine Blue	P.B.15:3			1.6	62	6.0-8.5	40-55	≤300
				1.58	62	6.0-8.5	40-55	≤300
711183				1.6	62	6.0-8.5	40-55	≤300
711283				1.58	62	6.0-8.5	40-55	≤300
Phthalocyanine Green	7031G	P.G. 7		1.87	60	6.0-8.0	32-42	≤300

Offset Ink													
Resistance													
Fastness Properties													
Application													
Light Fastness	Heat Resistance	Acid Fastness	Alkali Fastness	Solvent Fastness	Fluidity	Sheet-fed	Rotary	Tin-plate	UV				
7-8	280	5	5	5	±2	★	★	★	☆				
7-8	280	5	5	5	±2				★				
7-8	280	5	5	5	±2	★	★	★					

Solvent Ink								
Series	Colour Index No.	Full Shade	Reduced Shade	Physical Properties				
				Density g/cm ³	Specific Surface (area m ² /g)	PH Value	Oil Absorption g/100g	Conductivity us/cm
Phthalocyanine Blue	P.B.15:3			1.59	62	6.0-8.5	40-55	≤300
				1.60	64	6.0-8.8	35-50	≤300
709983				1.59	62	6.0-8.5	40-55	≤300
901784	P.B.15:4			1.60	64	6.0-8.0	35-50	≤300
				1.60	64	6.0-8.0	35-50	≤300
Phthalocyanine Green	P.G. 7			2.01	60	6.0-8.0	32-42	≤300
				1.87	60	6.5-8.0	32-42	≤300
7035G				1.87	60	6.5-8.0	32-42	≤300

Solvent Ink													
Resistance													
Fastness Properties													
Application													
Light Fastness	Heat Resistance	Acid Fastness	Alkali Fastness	N-butanol Fastness	Butanone Fastness	Ethyl acetate Fastness	Table Printing	In Printing					
7-8	280	5	5	5	5	5	☆	☆					
7-8	280	5	5	5	5	5	★	★					
7-8	280	5	5	5	5	5	☆	☆					
7-8	280	5	5	5	5	5	★	★					

Water-based Ink								
Series	Colour Index No.	Full Shade	Reduced Shade	Physical Properties				
				Density g/cm ³	Specific Surface (area m ² /g)	PH Value	Oil Absorption g/100g	Conductivity us/cm
Phthalocyanine Blue	P.B.15			1.61	64	6.0-9.0	35-45	≤500
				1.59	62	6.0-8.5	40-55	≤300
8010BD				1.61	64	6.0-9.0	35-45	≤500
709283				1.59	62	6.0-8.5	40-55	≤300
Phthalocyanine Green	P.G. 7			1.87	60	6.5-8.0	32-42	≤300
				1.87	60	6.5-8.0	32-42	≤300
7020G				1.87	60	6.5-8.0	32-42	≤300

Water-based Ink													
Resistance													
Fastness Properties													
Application													
Light Fastness	Heat Resistance	Acid Fastness	Alkali Fastness	Alcohol Fastness	2-Propanol Fastness	Flex Printing	Sink Mark						
7-8	180	5	5	5	5	★	★						
7-8	280	5	5	5	5	★	★						
7-8	280	5	5	5	5	★	★						

KEVIN... Pigment of the Imagination